
Tapered Roofing Insulation



Alleguard's tapered roof insulation uses closed cell Expanded Polystyrene (EPS) offering cost effective performance. Slope and thickness of foam is custom manufactured for the specifics of each project for virtually limitless possibilities. Can be used in both new and retrofit applications for commercial, residential, institutional and industrial flat roofs.

Alleguard's tapered roof insulation has exceptionally low, long term, in-service water absorption properties allowing it to maintain its specified thermal performance and durability.



Alleguard Advantage

- Stable long term thermal resistance.
- Each panel is easy to handle due to the low weight, small size and can be easily cut.
- High design flexibility allows for more optimal sloping and drain placement to meet site specific conditions for more efficient drainage.
- Does not promote growth of mold and mildew.
- Can be combined with Envirosheet flat rigid insulation to act as fill to create a hybrid tapered insulation system.
- **Alleguard provides tapered roofing estimating services with detailed tapered layouts for quantity takeoff. Contact your local Territory Manager for additional information.

PRODUCT DATA SHEET

TAPERED INSULATION

Availability

Tapered roof insulation is available in a wide range of slopes ranging from 1/2" (13mm) up to 48" (1219mm). Standard board dimensions are 4x4' (1.2x1.2m).

Applications

- Flat roofs
- Low slope roofs
- Compatible adhered or ballasted systems
- Hybrid tapered roof insulation solutions
- Compatible with single-ply or built-up roofs

The maximum continuous operating temperature for tapered roof insulation is 158°F (70°C). EPS exposure to ultra violet (UV) is limited to a thin layer causing slight discoloration and surface dusting. The material underneath remains unaffected maintaining its properties. Prolonged exposure may cause minimal reduction in thickness. To avoid adhesion issues, apply the product right after board installation or remove the UV affected material by brushing/rasping the surface to expose unaffected EPS (avoid hydrocarbons and petroleum based products).

Warranty

Alleguard supports building owners, designers and contractors by offering a 20-year, limited thermal warranty on the tapered roof insulation product line. This warranty is available to the building owner at the time the building is completed and is transferable to any subsequent owner during the 20-year period.

Physical Properties Table									
	Standard	Units	TP10	TP13	TP15 (HD)	TP20 (HD)	TP25 (HD)	TP30 (HD)	TP40 (HD)
Specification for Rigid Polystyrene Insulation	ASTM C578		Type I	Type VIII	Type II	Type II	Type IX	Type IX	Type XIV
	CAN/ULC-S701		Type 1	Type 1	Type 2	Type 2	Type 3	Type 3	Type 3
Thermal Resistance ¹	ASTM C518 @ 75°F (24°C)	F.ft ² .hr/Btu (m ² K/W)	3.9 (0.69)	3.9 (0.69)	4.0 (0.70)	4.2 (0.74)	4.3 (0.76)	4.4 (0.77)	4.4 (0.77)
Compressive Strength	ASTM D1621 @ 10% Strain	psi (kPa)	10 (69)	13 (90)	15 (104)	20 (138)	25 (172)	30 (207)	40 (276)
Water Absorption (Max.)	ASTM D2842	%	4.0	3.0	3.0	3.0	2.0	2.0	2.0
Water Vapor Permeance (Max.)¹	ASTM E96	US perms (ng/Pa.s.m²)	5.00 (287)	3.50 (200)	3.50 (200)	3.50 (200)	2.27 (130)	2.27 (130)	2.27 (130)
Flexural Strength (Min.)	ASTM C203	psi (kPa)	25 (173)	30 (208)	35 (242)	35 (242)	50 (345)	50 (345)	60 (414)
Dimensional Stability (Max.)	ASTM D2126	%	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Limiting Oxygen Index (Min.)	ASTM D2863	%	24	24	24	24	24	24	24
Density	ASTM D1622	lb/ft³ (kg/m³)	1.00 (16)	1.15 (18)	1.35 (22)	1.50 (24)	1.80 (29)	2.00 (32)	2.50 (40)
Surface Burning	ASTM E84 ²								
Characteristics	Flame Spread Index (FSI)		≤25	≤25	≤25	≤25	≤25	≤25	
	Smoke Developed Index (SDI)		≤450	≤450	≤450	≤450	≤450	≤450	
	CAN/ULC-S102 ²								
	Flame Spread Index (FSI)		≤210	≤210	≤210	≤210	≤210	≤210	
	Smoke Developed Index (SDI)		≥500	≥500	≥500	≥500	≥500	≥500	
	¹ Measurement per 1" (25mm) of thickness ² For thicknesses up to 4" or 100mm								

